

PRODUCT DATA SHEET

POLYPROPYLENE

BE961MO

POLYPROPYLENE BLOCK COPOLYMER FOR INJECTION MOULDING

DESCRIPTION

BE961MO is a heterophasic copolymer. This product is characterized by an optimum combination of high stiffness, low creep and very high impact strength.

This product uses Borstar Nucleation Technology (BNT) to increase productivity by cycle time reduction.

Articles produced with this product have very good demoulding properties, well-balanced mechanical properties and excellent dimension consistency with respect to different colours.

APPLICATIONS

Crates and boxes
Pails
Luggage

Ice cream containers
Appliances
Technical parts

SPECIAL FEATURES

High Impact strength, even at low temperatures
Excellent dimensional stability
Good flow behaviour

PHYSICAL PROPERTIES

Property	Typical Value	Test Method
Density	900-910kg/m ³	ISO 1183
Melt Flow Rate (230°C/2.16kg)	12g/10min	ISO 1133
Tensile Modulus (1mm/min)	1200MPa	ISO 527-2
Tensile Strain at Yield (50mm/min)	5,3%	ISO 527-2
Tensile Stress at Yield (50mm/min)	23MPa	ISO 527-2
Flexural Modulus	1250MPa	ISO 178
Tensile Strain at Yield	5.3%	ASTM D638
Tensile Stress at Yield	23MPa	ASTM D638
Flexural Modulus(by 1% secant)	1200MPa	ASTM D790A
Charpy Impact Strength, notched (23°C)	14kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20°C)	7kJ/m ²	ISO 179/1eA
IZOD Impact Strength, notched (23°C)	160J/m	ASTM D256
IZOD Impact Strength, notched (-20°C)	75J/m	ASTM D256
Heat Deflection Temperature(0,45MPa)**	92°C	ISO 75-2
Vicat Softening Temperature(Method A)***	144°C	ISO 306
Hardness, Rockwell(R-scale)	87	ISO 2039-2

*Data should not be used for specification work

**Measured on injection moulded specimens acc. to ISO 1873-2

*** Measured on injection moulded specimens, conditioned at 23°C and 50% Rel. Hum.

PROCESSING CONDITIONS

BE961MO is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature: 210 - 260°C
Holding pressure: 200 - 500bar As required to avoid sink marks
Mould temperature: 10 - 30°C
Injection speed: As high as possible
Shrinkage 1 - 2%, depending on wall thickness and moulding parameters

STORAGE

BE961MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage can be found in Safety Information Sheet (SIS) for this product

SAFETY

The product is not classified as a hazardous preparation.

Please see our Safety Information Sheet (SIS) for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borouge representative.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Information Sheet
Statement on chemicals, regulations and standards
Statement on compliance to food contact regulations

STANDARDS

Borouge is certified to various ISO standards, please refer to Borouge.com for more information.

DISCLAIMER

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose.

The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borouge products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.